

EFFECT OF CUTTING PARAMETERS ON DUST EMISSION AND SURFACE ROUGHNESS DURING HELICAL PLANING RED OAK WOOD

B Ugolino, RE Hernández - [Wood and Fiber Science, 2017](#) - researchgate.net

Cutting parameters can influence the chip thickness and resulting dust emission and surface quality during wood machining. The purpose of this study was to evaluate the effect of cutting parameters on the airborne dust emission (0.1-15 µm) and surface roughness ...

☆  Citat de 1 ori [Articole cu conținut similar](#) [Toate cele 3 versiuni](#) 

Influence of milling and sanding on beech wood surface properties. Part I. Surface morphology

J Küdela, L Javorek, L Mrenica - *Annals of Warsaw Agricultural ...*, 2016 - researchgate.net
This work investigates the influence of beech wood mechanical treatment on specific surface properties of this wood. The aim of this part has been to recognise milling and sanding-induced physical modifications of beech wood surface morphology assessed through ...

☆  Citat de 4 ori [Articole cu conținut similar](#) [Toate cele 2 versiuni](#)

The influence of some factors on cutting force and surface roughness of wood after sanding

L Javorek, J Küdela, J Svoreň, M KRAJČOVIČOVÁ - *Proligno*, 2015 - researchgate.net
This contribution presents results of an experimental research on sanding. With a sample of oak being the experimental material, sanding was carried out on radial, tangential and transversal surface of the piece. The impact force was changed on three levels (21 N, 41 N ...

☆  Citat de 2 ori [Articole cu conținut similar](#) [Toate cele 7 versiuni](#) 

THE INFLUENCE OF MILLING AND SANDING ON WOOD SURFACE MORPHOLOGY

J Küdela, L Mrenica, L Javorek - *Acta Facultatis Xylogiæ Zvolen res ...*, 2018 - df.tuzvo.sk
The influence of milling and sanding on surface morphology of beech and spruce wood is investigated in the paper. Wood morphology was assessed through roughness and waviness parameters. The experimental results showed that the two wood surface ...

☆  [Articole cu conținut similar](#) [Toate cele 2 versiuni](#) 

The influence of machining process on wood surface roughness

H Çota, D Ajdinaj, B Habipi - *Albanian Journal of Agricultural ...*, 2017 - sites.google.com
In this research, the effect of different machining processes on wood surface roughness was studied. There were applied three main furniture manufacturing processes, respectively planing, routing and sanding. The sanding process was applied twice, respectively with ...

☆  [Articole cu conținut similar](#) [Toate cele 3 versiuni](#) 

INFLUENCE OF PRESSING PARAMETERS ON SURFACE PROPERTIES OF COMPRESSED BEECH WOOD

J Küdela, M Rešetka, P Rademacher... *WOOD ...*, 2017 - woodresearch.sk
The influence of press conditions on wood properties was studied on demilled beech wood. The pressing parameters affected the surface properties of wood specimens: hardness, roughness, and colour change. The effects and impacts varied among the individual ...

☆  [Articole cu conținut similar](#) 



THE INFLUENCE OF SOME FACTORS ON CUTTING FORCE AND SURFACE ROUGHNESS OF WOOD AFTER SANDING

Lubomír JAVOREK

Technical University in Zvolen
T. G. Masaryka 24, 960 53 Zvolen, Slovak rep.
++421 45 5206 546, Fax: ++421 45 5320015, E-mail: lubomir.javorek@tuzvo.sk

Jozef KÚDELA

Technical University in Zvolen
T. G. Masaryka 24, 960 53 Zvolen, Slovak rep.
++421 45 5206 334 Fax: ++421 45 5320015, E-mail: jozef.kudela@tuzvo.sk

Ján SVOREŇ

Technical University in Zvolen
T. G. Masaryka 24, 960 53 Zvolen, Slovak rep.
++421 45 5206 548, Fax: ++421 45 5320015, E-mail: jan.svoren@tuzvo.sk

Mária KRAJČOVIČOVÁ

Technical University in Zvolen
T. G. Masaryka 24, 960 53 Zvolen, Slovak rep.
++421 45 5206 575, Fax: ++421 45 5320015, E-mail: maria.krajcovicova@tuzvo.sk

Abstract

This contribution presents results of an experimental research on sanding. With a sample of oak being the experimental material, sanding was carried out on radial, tangential and transversal surface of the piece. The impact force was changed on three levels (21 N, 41 N and 58.5 N), the grain size of sanding belt in four levels (40, 60, 80, 100). The constant parameters were: cutting speed 200 m·min⁻¹, moisture content of the sample 12%. The cutting force and surface roughness were measured and cutting force was recalculated to 1 mm of width of sanding belt. The cutting force was: within 0.80 till 1.0 N·mm⁻¹ for oak, impact force 21 N, for all surfaces and for all grain size; within 0.47 till 0.54 N·mm⁻¹ for oak, impact force 41 N, for all surfaces and for all grain size; within 0.23 till 0.26 N·mm⁻¹ for oak, impact force 58.5 N, for all surfaces and for all grain size. Surface roughness alternated within limits 4.42 μm – 14.43 μm depending up grain size, impact force and character of sanded surface. The minimum values for grain size 100, transversal surface and impact force 21 N; maximum values for grain size 40, tangential surface and impact force 41 N. Surface roughness was measured in perpendicular direction to cutting direction.

Key words: sanding of wood; impact force; cutting force; surface roughness.

INTRODUCTION

Sanding of wood is a very frequent object of research in the world. The reason is that sanding is usually the last operation of surface modification before lustering or painting and the technology may improve surface quality and ensure dimensional accuracy of workpiece. The quality of sanding surface directly determines the final effect: as for as both the potential customer's interest (i.e. the success on the market) and the resistance against weather conditions are concerned.

Sanding can be characterized as machining with a lot of cutting wedges with non-defined geometry. This geometry is coined by grains of the abrasive material, joined together by means of a binding material.

In general, the rake angle of grains is crushingly negative, the chip is modified under a big angle φ_1 in the zone of machining and the temperature in this area may rise, by **Banský, Naščák, Wieloch** (1999), up to 230°C; They tested the influence of temperature and grain size (P80 and P120) on the surface roughness of the chipboard and MDF board. The influence of temperature on the surface roughness was the most intensive for grain size P80.

The significance of sanding technology arises together with the evolution and production more and more productive grinders and the original purpose sanding machine for finishing is extended for roughness too. In this case, sanding may compete with other methods of machining.

The main characteristics of sanding according to **Driensky** (1986) are:

- irregular stylus fillet,
- irregular geometrical shape,
- high hardness and termical resistance,
- high cutting speed (from 30 mps until 120 mps),
- short-lasting contact with the machined workpiece (cca 0,0001 s),
- small size of grains (from 0,003 mm to 3 mm),
- very small cross section of the chip (from 10^{-3} mm² until 10^{-5} mm²),
- wearing of grains during the sanding process, i.e. degresion of the cutting property.

A model of the chip removing including a definition of the basic geometry according to **Maslov** (1979) is displayed in Fig. 1.




Fig. 1.
Model of the chip removing (Maslov 1979)

α_n – clereance angle, β_n – wedge angle, γ_n – rake angle, r_n – radius of cutting wedge, ϕ – angle of the primary plastic deformation, a_z – depth of the grain penetration into the material, v_c – cutting speed

Influence of the grain size on the surface roughness was in focus of **Bahchevandziev a Manev** (1999) who used a chip board covered with veneer from beech and pine as their experimental material. The granularity of abrasive papers were P100 and P150, respectively P120, P150, P180 and sanding was carried out in parallel and vertically compared with fibres. The experiment confirmed significant influence of last sanding direction to final surface roughness.

Očkajova and Siklienka (2000) solved influence of the wood species, orientation of wood's fibres, and sort of the grinding material on the volume of wood removed per minuta. They stated a correlation between removed material and species of wood, grain size, as well as fibre of wood orientation.

The research objective of **Ayrimis, Candan, Akbulut, Balkiz** (2010) was to investigate the effects of sanding on the surface properties of the medium density fiberboard (MDF) panels made from *Rhododendron ponticum* L. wood. The MDF panels were sanded with different sizes of the sand paper grit: P60; P60+P80; or P60+P80+P120 grit. Surface absorption and surface roughness of the MDF panels were determined on the basis of the EN 382-1 standard and ISO 4287 by using a fine stylus profilometer. The MDF surface sanded with a 60-grit size had a lower contact angle and more wettable surface compared to the surfaces sanded with P60+P80+P120 grit sizes.

The paper by **Fotin, Cismaru, Marthy, Brenci, Coseranu** (2011) presents the results of experimental research studies dealing with the power consumption during the process of sanding birch wood with grain sizes of P60, P80, P100 and P120 with regard to three processing directions (parallel, perpendicular and at 45° angle to the wood structure orientation). The industrial experiments were performed at NIKMOB Company, on the wide belt sander machine using an electronic device and a data acquisition logger in order to record the power consumption. The factorial experiment with two variables (feed speed and cutting depth) was used.

Fotin et al. (2013) presented results of the experimental research on the quality of birch wood surfaces after sanding them with P60, P80, P100 and P120 grains sizes, analyzing the roughness parameters of the sanded surfaces in each phase. The birch wood specimens were sanded parallelly, perpendicularly and with a 45-degrees inclination towards the wood fibres.

The paper by **Jaić, Palija, Dobić** (2010) presents a research of the influence of the system of surface finishing on the most significant decorative properties of the dried film: color and gloss. The samples were made from two species of Paulownia (*Paulownia elongata* and *Paulownia fortunei*).

In the study by **Richter, Feist, Knaebe** (1995), analysis results of a relationship between the morphological structure of the outside wood layer (surface roughness), and the performance of coatings are given. The surface roughness of five roughness categories (processed by planing, sanding, and bandsawing) on three wood substrates (vertical- and flat-grained western redcedar and flat-grained southern yellow pine) was determined by stylus tracer measurements.

The aim of the reasearch of **Tian and Li** (2014) was to explore the correlation between the sanding efficiency and the surface quality. As testing material were used Manchurian ash, Birch and MDF board, technological conditions were in longitudinal and transverse direction to wood fibres and grain sizes of paper P60 and P100 as influencing factors, analyzed their influence on the sanding efficiency and the surface quality. Results indicated that the highest sanding efficiency was obtained by MDF when sanded with the P60 grain size abrasive belt, Manchurian ash acquired the lowest sanding efficiency when sanded with the P100 grain size abrasive belt in longitudinal direction. Moreover, the lowest Ra was yielded by Manchurian ash when sanded with the P100 grain size abrasive belt in transverse direction; MDF gained the highest Ra when sanded with the P60 grain size abrasive belt. It also could be noted that there was not a visible correlation between sanding efficiency and surface quality in all cases of the study, but the belt should be replaced when the material removal rate decreased to a certain level in order to acquire better product quality and economic efficiency.

Sanding of non- and hydro-thermally treated oak was in the focus of experiments by **Wilkowski et al.** (2011). They used an equipment with a loaf grinding bit, and a CNC machine with vaccum clamping system for fixing of worpiece. For wood machining, following parameters were used: granulation of abrasive paper P40, dimensions of grinding bit 30mm/60mm, depth of cut 1mm, feed speed 1mpm and rotational spindle speed 2000rpm.

The experimental results from sanding different wood species (conifers, broadleaves) with known internal anatomical characteristics were used in the experiment by **Magoss** (2013): 4 different grain sizes were applied in the range of P80 and P240 were presented in diagrams showing the basic relationships between the surface roughness parameters and grain diameters (4 different grain sizes), the roughness parameters and structure number for all wood species, and internal relationships between roughness parameters.

According to **Gurau** (2013) and **Gurau** (2014) sanded wood surface have different irregularities caused by machining and wood anatomy; the wood anatomy was excluded from the roughness profiles using a method based on the Abbot-curve. Latewood was smoother than earlywood with the greatest ratio in oak, followed by spruce and beech. The author used paper with P180 and P120 grain sizes, diferent for various samples.

The effects of wood dust on humen health were analysed by **Darii and Badescu** (2011). Spruce, beech and MDF were used as experimental materials, cutting speed was constant (18 mps) and granularity of used papers was P40, P60, P80, P100 P150. From all the parameters the feed speed, pressure, moisture content and density of the material have a considerable influence on the resulted volume of chips.

The influence of the impact force (21 N, 41 N and 58.5N), feed speed (50mpm, 150 mpm, 200 mpm), sample of wood (spruce, oak, beech), type of the surface (radial, tangential, transversal), and size of the grids (P40, P60, P80, P100) on the cutting force and surface roughness were in focus of **Šuniar and Javorek** (2013) research. In this research, 648 pieces for every wood species were used, i.e. 1944 pieces altogether. This paper presents a reduced overview of the research – for oak, cutting speed 200 mpm only.

OBJECTIVE

The main objective of the presented research was to evaluate cutting force and surface roughness as functions of the cutting speed, impact force, species of wood and sanding direction in the face of wood's fibres orientation.

MATERIAL, METHOD, EQUIPMENT

English oak (*Quercus robur* L.) was used as experimental material. The samples were prepared as a box of 60 mm x 60 mm x 60 mm so, that its sides functioned as radial, tangential and transversal surfaces. Oak is one of the most important hard wood species in Slovakia (preceded by beech and followed by maple); at present it covers app. 10.7 % of the Slovak forest area. **Klement et al** (2011) declares physical properties of the raw material with moisture content 12%. Some of the properties are shown in the Table 1.

Table 1

Physical properties of the experimental material

Density [kg.m ⁻³]		Moisture content of green wood [%]		Fibre-saturation point humidity [%]
in absolute dry status ρ_0	reduced in fresh status ρ_{rc}	sapwood	adult wood	
390 / 650 / 930	550	70 - 100	60 - 90	32 - 35
Linear shrinkage in direction				Volumetric shrinkage
longitudinal		radial	tangential	
0.4		4.0	7.8	
				12.2

The goal of the experiment was to state the influence of grain size (P40, P60, P80, P100), impact force, (21 N, 41 N, 58.5N), cutting speed (200 mpm), and feed direction toward to wood's fibres (parallel or perpendicular) on the cutting force and surface roughness. The surfaces of the experimental samples were defined as tangential (T), radial (R) and transversal (P).




Fig. 2.

a - Definition of machined surfaces; b - Detail of sanding; c - Surface roughness measuring

Piezoelectric measuring system (Fig. 3.) made by Kistler (Kistler Instrumente AG, Switzerland) was used for measuring the cutting force. The system was also used for checking the impact force. The basic parts of the system were:

1. Dynamometer 9275B (parameter see Table 2).
2. Multichanel Charge Amplifier 5070A.
3. A/D Converter – DAQ System 5657A1.
4. PC + softver DynoWare.




Fig. 3.

Scheme of the measuring chain

Table 2

Dynamometer typ 9257A – chosen technical parameters

Range force application	F_x, F_y, F_z	kN	- 5 ... 5
Overload F_x and $F_y \leq 0,5 F_z$	F_x, F_y, F_z	kN	-7,5 / 7,5
	F_z	kN	-7,5 / 15
Response threshold		N	< 0,01
Sensitivity	F_x, F_y	pC/N	$\approx -7,5$
	F_z	pC/N	$\approx -3,7$
Linearity (all ranges)		% FSO	$\leq \pm 1$
Rigidity	C_x, C_y	kN/ μ m	>1
	C_z	kN/ μ m	>2
Natural frequency	$f_n(x, y, z)$	kHz	$\approx 3,5$
Natural frequency (mounted on flanges)	$f_n(x, y)$	kHz	$\approx 2,3$
	$f_n(z)$	kHz	$\approx 3,5$
Operating temperature range		$^{\circ}$ C	0 ... 70
Temperature coefficient of sensitivity		% / $^{\circ}$ C	- 0,02
Capacitance (of channel)		pF	220
Ground insulation		Ω	$> 10^8$




Fig. 4.
The records of the impact force (F_z) and cutting force (F_y)

RESULTS AND DISCUSSION

A fullfactorial experiment was carried out, i.e. for all variations of all independed variables. Involved results valid for one-factorial analyse. Cutting force was recalculated to 1mm-wide sanded surface, therefore quoted unit of force is $N \cdot mm^{-1}$. The surface roughness was measured in the direction of cutting speed and in the direction perpendicular to cutting speed.

Fig. 5 displays the influence of impact force ($A=58.5N$), grain size of belts and type of the surface (R, T, P) on the cutting force. The values of forces for radial and tangential surfaces are very similar – only for grain size 40, there is a diference of $0.12N \cdot mm^{-1}$. It looks like very small, but for a 300 mm-wide board, for instance, it is 36 N, and for a 1000 mm-wide bioboard it is 120N. Therefore it is important to bear in mind this fact when processing wider plates.




Fig. 5.

Influence of grain size and impact force A on the cutting force (oak, $v_c = 200$ mpm)

Values in the graph in Fig. 6 display analogical independent variables as the graph in Fig. 5. Nevertheless, the value of impact force was $B=41$ N, i.e. 1.4-time lower. The graphs look similar but the value of cutting force was lower by 40% till 50%.




Fig. 6.

Influence of grain size and impact force B on the cutting force (oak, $v_c = 200$ mpm)

The graph in Fig. 7 illustrates results received during sanding with impact force $C=21$ N, i.e. 2.7-times smaller than force A and 2-times smaller than force B. This is evident in the decrease of the cutting force. However, if we compare radial, tangential and transversal surfaces, the cutting force increases practically in every case.




Fig. 7.

Influence of grain size and impact force C on the cutting force (oak, $v_c = 200$ mpm)

The evaluation of surface roughness is in follows part; as arithmetic average of absolute values, i.e. parameter Ra. For measuring the surface roughness, Surfcom 130A was used; contact measuring system with radius of stylus tip $2\pm 0.5\mu\text{m}$, cut-off was 0.8mm, evaluated length 30mm. The influence of the measure direction was very significant (see records in Fig. 8. resp. in Fig. 9.). Values for perpendicular direction were cca 2.5-times higher. (This paper only presents results from perpendicular direction measuring).




Fig. 8. Surface roughness in direction to sanding direction




Fig. 9.

Surface roughness in perpendicular direction to sanding direction

The graph in Fig.10. presents the average values of surface roughness as dependent on impact force, type of surface and grain size of oak.




Fig. 10.

Influence of grain size, impact force and sanded surface on the surface roughness in direction perpendicular to cutting direction (oak, $v_c = 200 \text{ mpm}$)

From this graph, a very considerable influence of grain size on the value of roughness is evident. It was true of the whole research. For example, for radial surface applies that the change granularity from 1P00 to P40 surface roughness will change (increase) in 89.5% (for force A), in 92.3% (for force B), in 51% (for force C). The average value is nearly 77.2%.

For tangential surface it is (the change granularity from P100 to P40) roughness will increase in 94.4% (for force A), in 151% (for force B), in 146% (for force C). The average value is practically 130.5%.

For transversal surface for the same granularity (P100 or P40) roughness will increase in 78% (for force A), in 98% (for force B), in 123% (for force C). The average value is almost 100%.

CONCLUSIONS

The experiment confirmed the dependency of the cutting force on grain size, impact force and fibres orientation compared with direct of cutting velocity, including the type of the sanded surface (radial, tangential, transversal). These differences of force were not very considerable.

Surface roughness very significantly depends on grain size and impact force. Surface roughness has effect on the speed of liquid interpenetration to wood.

ACKNOWLEDGEMENT

1. Part of this article was created within the framework of Grand project No. 1/0893/13 Surface facilities and interaction in interface of phases wood - liquid as result of author's research activity with widespread favour of agency VEGA-SR. Supervisor: Jozef Kúdela.

2. Experimental devices used for forces measuring were obtained with strong support of The Ministry of Education, Science, Research and Sport of the Slovak Republic and while solution of programme OPVaV-2009/5.1/03-SORO, Research and Development, Axe 5.1 Building of infrastructure of higher schools and modernization of their interior equipment with a view to improve the conditions of the education process.

REFERENCES

Ayrlimis N et al. (2010) Effect of Sanding on Surface Properties of Medium Density Fiberboard. *Drvna Industrija* 61(3):175-181. <http://drvnaindustrija.sumfak.hr/pdf/Drv/20Ind/20Vol/2061/203/20Ayrlimis.pdf>. (access 2015-02-27)

Bahchevandziev K, Manev T (1999) Effects of sanding and staining on the surface quality of veneered boards. In: *Zborník referátov z medzinárodnej vedeckej konferencie "Stroj-Nástroj-Obrobok"*, Nitra, pp. 7-11.

Banský M et al. (1999) The testing of sanding papers from point of their durability. (In Slovak: Testovanie brúsnych papierov z hľadiska ich životnosti.) In: *Zborník referátov z medzinárodnej vedeckej konferencie "Stroj-Nástroj-Obrobok"*, Nitra, pp.19-22.

Darii I, Badescu LAM (2011) Research on the emission of dust resulting from sanding process for solid Spruce, Beech and MDF panel. In: *Recent Advances in Environment, Energy Systems and Naval Science*. WSEAS Press, 2011. ISBN 978-1-61804-032-9, pp. 288-296.

Csiha C (2004) Study of wood surface roughness on P and r profile focused on big porous species. Doctoral thesis. University of West Hungary. Sopron. http://ilex.efeh.hu/PhD/fmk/csihacs/tz_en1005.pdf, (access 2015-02-27)

Driensky D et al. (1986) *Strojní obrábění I*. SNTL Praha. Pp. 422, ISBN 04-238-86.

Fotin A et al. (2011) Experimental research concerning the power consumption during the sanding process of birch wood. In: *2011 Proceedings of International conference of scientific paper*. Afases, Brasov, 26-28 May. Pp. 771-778.

http://www.afahc.ro/ro/afases/2011/eng/4.2/FOTIN_Cismaru_Marthy_Brenci_Cosereanu.pdf. (access 2015-02-27)

Fotin A et al. (2013) Influence of the processing parameters upon the birch wood sanded surfaces. In: *PRO LIGNO*, 9(4):760-770, ISSN 2069-7430, ISSN-L 1841-4737. http://www.proligno.ro/ro/articles/2013/4/Fotin_final.pdf (access 2015-02-27)

Gurau L (2013) Analyses of roughness of sanded oak and beech surface. *PRO LIGNO*, 9(4):741-750, ISSN 2069-7430

Gurau L (2014) The influence of earlywood and late wood upon the processing roughness parameters at sanding. *PRO LIGNO*, 10(3):26-33, ISSN 2069-7430

Hiziroglu S (1996) Surface Roughness analysis of wood composites: A stylus Method. Forest Products J. 46(7/8):67-72.

Jaić M et al. (2010) The influence of surface finishing of paulownia siebold et zucc. on the decorative properties of lacquered surface. <http://idk.org.rs/wp-content/uploads/2015/01/2-2014/Jaic%20rad.pdf> (acces 2015-02-27)

Klement I et al. (2011) Dub letný. In: Základné charakteristiky lesných drevín – spracovanie drevnej suroviny v odvetví spracovania dreva. Národné Lesnícke Centrum, pp.82 ISBN 978-80-8093-112-4. <http://www.nlcsk.sk/files/1708.pdf>. (acces 2015-02-27)

Magoss E (2013) General regularities of the surface roughness sanding solid woods. In Proceedings 21st IWMS Tsukuba, Japan, Pp. 325-332.

Maslov JN (1979) Teorie broušení kovů. (Theory of metal sanding). SNTL Praha. pp. 248. 04-225-79.

Očkajová A, Siklienka M (2000) The influence of chosen factors of wood sanding upon the efficiency of sand belt. In: Wood Research. 45(2):33-38.

Richter K et al. (1995) The effect of surface roughness on the performance of finishes. Part 1. Roughness characterization and stain performance. Forest Product J. V. 45, 7/8. <http://www.fpl.fs.fed.us/documnts/pdf1995/richt95a.pdf>. (acces 2015-02-27)

Schultz MP (2002) The Relationship Between Frictional Resistance and Roughness for Surfaces Smoothed by Sanding. Department of Naval Architecture & Ocean. Engineering, United States Naval Academy, Annapolis, MD 21402. <http://www.dtic.mil/dtic/tr/fulltext/u2/a575300.pdf>. (acces 2015-02-27)

Šuniar P (2013) The influence of chosen factors to forces factors and surface quality during sanding. (In Slovak: Vplyv vybraných faktorov na silové parametre a kvalitu povrchu pri brúsení). Diploma thesis. Technical University in Zvolen. Faculty of Environmental and Manufacturing Technology. Pp73. Supervisor: Ľubomír Javorek.

Tian M, Li L (2014) Study on influencing factors of sanding efficiency of abrasive belts in wood materials sanding. In.: Wood Research 59(5):835-842. <http://www.centrumdp.sk/wr/201405/20140512.pdf>. (acces 2015-02-27)

Wilkowski J et al. (2011) Surface roughness after sanding of thermally modified oak wood. In. Annals of Warsaw University of Life Sciences – SGGW. Forestry and Wood Technology No 76, 2011: 208-211. <http://annals-wuls.sggw.pl/files/files/fwt/fwt2011no76art42.pdf>. (acces 2015-02-27).